

Formerly known as SOPRAFLASH STICK 20

# SOPRAFLASH STICK



WATERPROOFING

APPLICATIONS

ROOFS

TECHNICAL DATA SHEET 200610SCANE

(supersedes 200316SCANE)

## DESCRIPTION

SOPRAFLASH STICK is a base sheet membrane composed of SBS modified bitumen and a glass mat reinforcement. The surface is sanded and the self-adhesive underface is covered with a silicone release film.

## SURFACE PREPARATION

Surfaces must be clean, dry and free of loose particles. The membrane is installed over the substrate previously primed with one of the ELASTOCOL STICK primers.

## INSTALLATION

### SELF-ADHESIVE

SOPRAFLASH STICK is adhered to the substrate by peeling off the silicone release film.

Once the membrane is in place, apply pressure over the whole surface using a membrane roller to ensure a complete and uniform adhesion.

When completing the end lap, apply ELASTOCOL STICK primer over the last 150 mm (6 in) of the membrane before installing the next membrane.

Application temperatures: 0 °C (32 °F).

FOR COMPLETE INFORMATION ON PRODUCT INSTALLATION, PLEASE CONSULT YOUR SOPREMA REPRESENTATIVE.

## PACKAGING

Specifications	SOPRAFLASH STICK
Thickness	2.5 mm (98 mils)
Reinforcement	Glass mat
Dimensions	15 x 1 m (49 x 3.3 ft)
Weight	2.9 kg/m <sup>2</sup> (0.6 lb/ft <sup>2</sup> )
Selvedge width	100 mm (4 in)
Surface	Sanded
Underface	Self-adhesive, covered with a silicone release film

(All values are nominal)



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

TDS\_SOPRAFLASH\_STICK.indd

Formerly known as SOPRAFLASH STICK 20

# SOPRAFLASH STICK



WATERPROOFING

APPLICATIONS

ROOFS

TECHNICAL DATA SHEET 200610SCANE

(supersedes 200316SCANE)

## PROPERTIES

Properties	Standards	SOPRAFLASH STICK	
		BEFORE Heat Conditioning	AFTER Heat Conditioning
Strain energy, min MD/XD At 23 °C ± 2 °C (73.4 °F ± 3.6 °F) At -18 °C ± 2 °C (0 °F ± 3.6 °F)	CSA A123.23-15, Type A, Grade 3	1/1 kN/m (5.7/5.7 lbf/in) 0.5/0.5 kN/m (2.8/2.8 lbf/in)	2.1/0.5 kN/m (12/2.8 lbf/in) 0.5/0.4 kN/m (2.8/2.3 lbf/in)
Peak load, min MD/XD At 23 °C ± 2 °C (73.4 °F ± 3.6 °F) At -18 °C ± 2 °C (0 °F ± 3.6 °F)		12/13.5 kN/m (69/77 lbf/in) 23/21 kN/m (131/120 lbf/in)	18/16 kN/m (103/91 lbf/in) 21/21 kN/m (120/120 lbf/in)
Elongation at peak load, min MD/XD At 23 °C ± 2 °C (73.4 °F ± 3.6 °F) At -18 °C ± 2 °C (0 °F ± 3.6 °F)		6/7 % 4/4 %	8/5 % 3/4 %
Ultimate elongation, MD/XD At 23 °C ± 2 °C (73.4 °F ± 3.6 °F)		35/30 %	10/7 %
Dimensional stability, max MD/XD		±0.3/±0.1 %	
Low temperature flexibility, max MD/XD		-30/-30 °C (-22/-22 °F)	-18/-18 °C (0/0 °F)
Compound stability at 91 °C (196 °F)		107/107 °C (225/225 °F)	
Water vapour transmission	ASTM E96 (Procédure B)	< 2.5 ng/Pa•s•m <sup>2</sup> (< 0.04 perm)	

(All values are nominal)

## STORAGE AND HANDLING

Rolls must be stored upright, with the selvedge side on top. If the products are stored outdoors, cover them with an opaque protection cover after removal of the delivery packaging.



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

TDS\_SOPRAFLASH\_STICK.indd